

VOLTAGE RATING: 600 volts (rms) at sea level ACCELERATED AGING: 300 ± 3°C for 7 hours BLOCKING: 200 ± 3°C for 6 hours DIELECTRIC WITHSTAND: 1500 volts (rms), 60 Hz FLAMMABILITY: Procedure 1, 3 seconds (maximum), 3 inches (maximum); no flaming of facial tissue JACKET COLOR: White preferred JACKET COLOR: White preferred JACKET ELONGATION AND TENSILE STRENGTH: Elongation, 50% (minimum) Tensile Strength, 5000 lbf/in² (minimum) JACKET FLAWS:

Spark Test, 1000 Volts, 60 Hz (rms) Impulse Dielectric Test, 6.0 kV (peak) LIFE CYCLE: 230 ± 3°C for 500 hours LOW TEMPERATURE-COLD BEND: -65 ± 2°C for 4 hours SHIELD COVERAGE: 85% (minimum) VOLTAGE WITHSTAND: (Post Environmental) 1000 volts (rms), 60 Hz, 1 minute

1/ PART NUMBER:

The "*" in the part numbers above shall be replaced by color code designators with a slash separating the component wire colors and a dash separating the component wire colors from the jacket color.

Example: AWG 20, white component wire; white jacket; 55A1816-20-9-9

NOTE: Nominal values are for information only. Nominal values are not requirements.

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. TE Connectivity also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer. 1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. HOWEVER, DUE TO LENGTH LIMITATIONS OF THE RAYCHEM PART NUMBER, AN ALTERNATIVE COLOR CODE MAY REPLACE MIL-STD-681 COLOR CODE DESIGNATORS. (EXAMPLE: "901/902..." MAY BE REPLACED BY "Axxx".) OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER. Page 1 of 1 DIMENSIONS ARE IN INCHES AND, UNLESS OTHERWISE DESIGNATED, ARE NOMINAL THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID. TAKES AND ALTERNATION STATES AND ALTER AND ADDITIONAL REPORT OF THE DIMENSION ARE IN 1-450--581-6297

© 2024 TE Connectivity. All rights reserved.