| | SPECIFICA | TION CO | ONTRO | OL DRAWIN | G | SCD | 55A | 1841 |
|-------|---|--|-------|-----------|------|-----------------|----------|------|
| Title | FOUF | FOUR CONDUCTOR CABLE, SHIELDED, JACKETED, GENERAL PURPOSE, 600 VOLT | | | | Date 3-18-19 | Revision | E |
| | This specification sheet forms a part of the latest issue of Raychem Specification 55A. | | | | | | | |
| | COMPONENT WIRES - 55A0811 SHIELD - TIN-COATED COPPER JACKET - RADIATION-CROSSLINKED, MODIFIED ETFE | | | | | | | |
| | | CABLE CONSTRUCTION DETAILS | | | | | | |
| | | | | | OUTE | | | |

| | CABLE CONSTRUCTION DETAILS | | | | | | |
|---------------------------|----------------------------|-------------------------|----------------------------|---------|----------------------------|---------|-------------------------------------|
| PART NUMBER <u>1</u> / | CONDUCTOR SIZE (AWG) | SHIELD SIZE (AWG) | JACKET THICKNESS (inch) | | OUTSIDE DIAMETER (inch) | | MAXIMUM WEIGHT (lbs/1000 ft.) |
| | | | MINIMUM | NOMINAL | NOMINAL | MAXIMUM | |
| 55A1841-26-* | 26 | 38 | .006 | .008 | .130 | .150 | 14.7 |
| 55A1841-24-* | 24 | 38 | .006 | .008 | .142 | .165 | 18.0 |
| 55A1841-22-* | 22 | 38 | .006 | .008 | .154 | .179 | 22.5 |
| 55A1841-20-* | 20 | 38 | .006 | .008 | .173 | .202 | 30.0 |
| 55A1841-18-* | 18 | 38 | .006 | .008 | .202 | .237 | 42.2 |
| 55A1841-16-* | 16 | 38 | .007 | .009 | .221 | .259 | 51.4 |
| 55A1841-14-* | 14 | 38 | .007 | .009 | .262 | .308 | 74.0 |
| 55A1841-12-* | 12 | 38 | .007 | .009 | .304 | .357 | 104. |
| 55A1841-10-* | 10 | 36 | .008 | .010 | .365 | .430 | 162. |
| 55A1841-8-* | 8 | 34 | .009 | .011 | .520 | .613 | 299. |
| 55A1841-6-* | 6 | 34 | .012 | .014 | .637 | .753 | 455. |

CABLE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C Maximum continuous conductor temperature VOLTAGE RATING: 600 volts (rms) at sea level ACCELERATED AGING: 300 ± 3°C for 7 hours BLOCKING: 200 ± 3°C for 6 hours DIELECTRIC WITHSTAND: 1500 volts (rms), 60 Hz FLAMMABILITY: Procedure 1, 3 seconds (maximum), 3 inches (maximum); no flaming of facial tissue JACKET COLOR: White preferred JACKET ELONGATION AND TENSILE STRENGTH: Elongation, 50% (minimum) Tensile Strength, 5000 lbf/in² (minimum) JACKET FLAWS: Spark Test, 1000 volts (rms) Impulse Dielectric Test, 6.0 kV (peak)

LIFE CYCLE: 200 ± 3°C for 168 hours LOW TEMPERATURE-COLD BEND: -65 ± 2°C for 4 hours SHIELD COVERAGE: 85% (minimum) VOLTAGE WITHSTAND (Post Environmental): 1000 volts (rms), 60 Hz, 1 minute

1/ PART NUMBER:

The "*" in the part numbers above shall be replaced by color code designators with a slash separating the component wire colors and a dash separating the component wire colors from the jacket color. Colors shown do not necessarily reflect the sequence of manufacturing.

Example: AWG 24, orange, green, blue, and white component wires; white jacket: 55A1841-24-3/5/6/9-9

NOTE: Nominal values are for information only. Nominal values are not requirements.

| Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. TE Connectivity also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer. | | | | | | | |
|--|--|--------------|--|--|--|--|--|
| 1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. HOWEVER, DUE TO LENGTH LIMITATIONS OF THE RAYCHEM PART NUMBER, AN ALTERNATIVE COLOR CODE MAY REPLACE MIL-STD-681 COLOR CODE DESIGNATORS. (EXAMPLE: "901/902" MAY BE REPLACED BY "Axxx".) OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER. | | | | | | | |
| | Raychem, TE Connectivity, and TE connectivity (logo) are trademarks. | | Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 | | | | |
| Page 1 of 1 | DIMENSIONS ARE IN INCHES AND, UNLESS OTHERWISE DESIGNATED, ARE NOMINAL | - TE | | | | | |
| | THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID. | connectivity | Phone: 1-800-522-6752 Fax: 1-650-361-6297 | | | | |

© 2019 TE Connectivity Ltd. family of companies. All Rights Reserved.