



SCD

Page

CABLE RATINGS AND ADDITIONAL REQUIREMENTS
TEMPERATURE RATING: 150°C Maximum continuous conductor temperature
VOLTAGE RATING: 600 volts (rms) at sea level
CROSSLINKED VERIFICATION: 300 ± 3°C for 1 hour DIELECTRIC WITHSTAND: 1500 volts (rms), 60 Hz
+ FLEXURE ENDURANCE: No failure at 200 cycles
FLUORIDE EXTRACTION: 70 ± 2°C for 168 hours, 150 ppm (maximum)
JACKET COLOR: White preferred JACKET ELONGATION AND TENSILE STRENGTH:
Elongation, 50% (minimum)
Tensile Strength, 5000 lbf/in² <i>(34.5 MPa)</i> (minimum) JACKET FLAWS:
Spark Test, 1000 volts (rms)
Impulse Dielectric Test, 6.0 kV (peak)
+ PULL THROUGH: No jacket tearing, no dielectric breakdown + SCRAPE ABRASION:
5000 cycles (minimum average) at 23 ± 2°C
3000 cycles (minimum average) at 70 ± 2°C
100 cycles (minimum average) at 150 ± 2°C SHIELD COVERAGE: 85% (minimum)
VOLTAGE WITHSTAND (Post Environmental): 1000 volts (rms), 60 Hz, 1 minute
1/ PART NUMBER:
The "*" in the part numbers on page 1 shall be replaced by color code designators
with a dash separating the component wire color from the jacket color. Example: AWG 24, white component wire; white jacket:
550TE1211-24-9-9

+ NOTE: The requirements for the Flexure Endurance, Pull Through, and Scrape Abrasion tests are applicable when tested on a 20 AWG single component, silver-coated copper flat braid shielded and jacketed cable only.

1/ See footer section on page 1